 논문

Eco-friendly Fabrication Process of Al-Ti-C Grain Refiner

Hoon Cho[†] and Bonghwan Kim

Liquid processing & casting technology R & D department, Korea Institute of Industrial Technology, Incheon, Korea

Abstract

알루미늄 합금의 미세조직 개량을 위한 목적으로 사용되는 Al-Ti-B 합금계의 미세화제는 재활용 과정에서 붕소(B)의 농축 (Agglomeration) 문제 및 Zr, Si, Cr 등을 함유하는 합금에서 미세화 효과가 급격히 감소하는 Poisoning effect 등이 지적되어 왔다. 최근에는 이를 대체할 수 있는 Al-Ti-C 합금계의 미세화제에 대한 연구가 활발한데 이는 TiC가 용탕 내에서 α -Al의 핵생성제로 직접 작용하는 점에 착안한 것이다. 한편, 이들 Al-Ti-B, Al-Ti-C 계의 미세화제는 그 제조공정에서 K_2TiF_6 를 이용함에 따라 불소함유 유해가스를 배출하여 환경 문제를 야기하고, 이를 포집/정화하기 위한 추가설비를 요구하게 된다. 따라서 대기 환경 오염 및 경제성 측면에서 유리한 미세화제의 친환경 제조기술에 대한 개발이 필요한 시점이다. 본 연구에서는 K_2TiF_6 를 사용하지 않고 용탕 내의 자발적 반응을 이용하여 환경 및 경제적 측면에서 유리한 Al-Ti-C 미세화제를 개발하고자 하였다. A3003 합금을 대상소재로 하여 개발된 Al-Ti-C 미세화제와 상용 Al-Ti-B 미세화제의 미세화 도달시간 및 fading 발생 등을 비교하였다. 본 연구를 통하여 개발된 Al-8.6Ti-0.025C 미세화제는 상용 Al-Ti-B 미세화제 보다 적은 첨가량에도 유사한 미세화 성능을 나타내었으며 용탕 유지시간 100 분까지도 fading 이 발생하지 않는 것을 확인하였다.

Key words : Grain refinement, Fadingless, Eco-friendly, $TiAl_3$, TiC.

(Received June 8, 2010 ; Accepted August 14, 2010)

1. Introduction

The Al-Ti-B type master alloys have been widely used for grain refinements of both wrought and foundry aluminum alloys [1-2]. Even though Al-Ti-B alloys have the excellent refining efficiency, many efforts has been made to develop alternative one due to both the agglomeration behavior of B and poisoning effects in Zr, Si, Cr-containing Al alloys. Recently, Al-Ti-C alloys have been attracted and researched as a promising refiner to achieve fine equiaxed grain structure in many Al alloys.

Meanwhile, the commercial grain refiners such as Al-Ti-B and Al-Ti-C have been fabricated by reaction of molten Al with K_2TiF_6 and graphite powder. This reaction produces the huge amount of environmentally harmful fluoride-containing fumes in the process. The expensive emission control system large enough to handle the periodic high emission rate as well as problems associated with boride agglomeration and poisoning effect in Al-Ti-B refiner have been remained as major concerns. Therefore, the great need for development of eco-friendly fabrication process of efficient grain refiner has been rising in wrought and foundry aluminum industry.

In the present study, it was aimed to develop and suggest an eco-friendly refining process of Al-Ti-C grain refiner and evaluate the refining characteristics as functions of holding time

and amount of addition in a A3003 alloy.

2. Experimental procedures

A non-toxic Al-Ti master alloy was melted in a graphite crucible, in which the in-situ formation of TiC was induced by the reaction of Al-Ti molten metal and carbon from graphite crucible. In order to optimize the reaction time, the carbon content, fraction of TiC and $TiAl_3$ were measured as a function of holding time in graphite crucible. The prepared molten alloy was gas-atomized to make an Al-Ti-C refiner in powder form. Through these processes as an eco-friendly fabrication process, the final form of the Al-Ti-C refiner was obtained. The chemical composition of the refiner was analyzed and confirmed as Al-8.6wt.%Ti-0.025wt.%C. The eco-friendly fabricated Al-8.6Ti-0.025C as well as commercial Al-5Ti-1B grain refiners were added to a molten A3003 alloy in order to evaluate and compare the refining efficiency, fading behavior and mechanical properties. The molten A3003 alloys were poured into a high purity alumina crucible and held at 750°C of an isothermal condition in a resistance furnace. The isothermally conditioned melts were directly poured into a cylindrical permanent mold to obtain the quenched microstructure as a function of holding time (1, 5, 10, 30, 60, 90, 120, 150, 180 and 240 minutes) at 750°C. The chemical compositions of A3003 alloys refined by

[†]E-mail : hoony67@kitech.re.kr

Table 1. Chemical compositions of A3003 alloys refined by the Al-8.6Ti-0.025C.

Alloy	Mn	Si	Fe	Cu	Zn	Ti	Al
A3003	1.9	0.4	0.51	0.2	0.12	0.049	Bal.
	2.1	0.5	0.58	0.3	0.19	0.15	

the eco-friendly made Al-8.6Ti-0.025C were analyzed and summarized in Table 1.

The grain size of the A3003 alloys refined by the Al-8.6Ti-0.025C and commercial Al-5Ti-1B refiner were measured by a line intercept method in a polarizing light microscope on polished sample. The representative macrostructures showing the refining efficiency in the whole area of the sample were taken after chemical macro-etching. The hardness of the refined by the Al-8.6Ti-0.025C and unrefined A3003 alloys were compared through the whole area of the sample to verify uniformity of refining ability. The tensile properties were measured as a function of content of the Al-8.6Ti-0.025C refiner to suggest the optimized level of the addition.

3. Results and discussion

The Fabrication of the Al-8.6Ti-0.025C grain refiner was carried out by melting of Al-10Ti master alloy in a graphite crucible in order to lead the in-situ formation of TiC phase by the reaction of the molten Ti and C from the graphite crucible. As shown in Fig. 1(a), the carbon content of the molten Al-Ti alloy in alumina crucible did not show any appreciable change during the holding period at 750°C. However, the carbon content of the molten Al-Ti master alloy in graphite crucible increased and reached the saturation point, about 150ppm of carbon after about 30min. of the holding time in the crucible. The source of the carbon in the graphite crucible seemed to be from the wall of the crucible in a elevated temperature. And

the carbon extracted from the graphite crucible was expected to be involved to the in-situ formation of TiC phase in the molten Al-Ti alloy.

Meanwhile, according to the binary Al-Ti phase diagram, the solubility of titanium in aluminum at 750°C is about 0.3wt.%. Therefore, titanium solute could be expected to be dissolved into molten aluminum as the holding time increases. The titanium solute can be supplied by the decomposition of the preexisting TiAl_3 phase in the molten Al-Ti alloy. Therefore, the dissolution of titanium solute into molten aluminum resulted in the decrease of preexisting fraction of TiAl_3 phase as shown in Fig. 1(b). On the contrary, the fraction of TiC phase of the molten Al-Ti alloy in the graphite crucible increased as the holding time increased at 750°C as shown in Fig. 1(b). It can be suggested that during the holding period, the in-situ reaction between the dissolved solute Ti from TiAl_3 and carbon from the graphite crucible produced the TiC particles consuming gradually the preexisting TiAl_3 particles. The reactions in the molten Al-Ti alloy during the holding time in the graphite crucible were summarized in the equation 1 and 2.

In order to identify and verify the phases formed in the molten Al-Ti alloy by the in-situ reaction during the holding period in the graphite crucible, the Al-8.6Ti-0.025C powder made by a gas-atomization of the molten Al-Ti alloy was subjected to X-ray diffractometry using Cu-K α radiation. Fig. 2 shows the XRD pattern of the fabricated Al-8.6Ti-0.025C powder. The peaks corresponding to α -Al, TiC and TiAl_3 were detected approving the presence of each phase. Especially, the presence of the TiC phase indicates the in-situ reactions between the dissolved Ti solute and carbon from the graphite crucible according to the equations 1 and 2.

Fig. 1. The variation of (a) the carbon content and (b) the fractions of TiC and TiAl_3 particle in the molten Al-Ti alloy as a function of the holding time at 750°C.

Fig. 2. XRD pattern of the Al-8.6Ti-0.025C powder made by the in-situ reaction and a gas-atomization process.

Fig. 3. Tensile strength and elongation of the A3003 alloy refined by the Al-8.6Ti-0.025C as a function of the content of Ti.

In order to evaluate the refining ability and behavior, the Al-8.6Ti-0.025C powder was added into A3003 alloy. The optimized amount of the addition was decided based on the combined analysis of mechanical properties and microstructure. For the comparison, the recommended amount of the commercial Al-Ti-B refiner was also added into A3003 and characterized together with the Al-8.6Ti-0.025C added specimen.

Fig. 4. The grain size of the A3003 alloys refined by the Al-8.6Ti-0.025C and the commercial Al-Ti-B as a function of the melt-treating time.

The A3003 alloys refined by either the Al-8.6Ti-0.025C or the commercial Al-Ti-B were quenched into a cylindrical steel mold after various melt-treating times and analyzed by a combined method of mechanical testing, optical microscopy and image analysis. The tensile properties of the A3003 alloy are shown in Fig. 3 as a function of the content of Ti solute. The tensile strength of the A3003 alloy increased up to the saturation value, about 115MPa even with 0.05Ti of a small addition, while the elongation did not show any appreciable change. Therefore, the optimized addition of the Al-Ti-C for the A3003 alloy was decided as the 0.05Ti.

Fig. 4 shows the variation of the grain sizes of the A3003 alloys refined by either the Al-8.6Ti-0.025C or the commercial Al-Ti-B refiner as a function of the melt-treating time in a high-purity alumina crucible. The added amount of the each refiner was converted to the added amount of Ti element and indicated on Fig. 4, respectively. The A3003 alloy refined by the commercial Al-Ti-B shows effective refining ability in a relatively delayed time, about 30min. However, the A3003 alloy refined by the eco-friendly fabricated Al-8.6Ti-0.025C shows almost equivalent refining ability in a relatively short time, a few minutes. It is also worth to mention that the amount of Ti addition by the Al-8.6Ti-0.025C was much smaller than

Fig. 5. The representative macrostructures of the A3003 alloys refined by (a) the commercial Al-Ti-B at about 10min. of the melt-treating time and (b)-(c) the Al-8.6Ti-0.025C refiner at about 10 and 120min., respectively.

that of the commercial Al-Ti-B refiner, meaning the efficient refining ability of the Al-8.6Ti-0.025C.

Fig. 5 shows the representative macrostructures of the A3003 alloys refined by (a) the commercial Al-Ti-B at about 10min. of the melt-treating time and (b)-(c) the Al-8.6Ti-0.025C refiner at about 10 and 120min., respectively. As shown in Figs. 5(a) and (b), the A3003 alloy refined by the Al-8.6Ti-0.025C shows a fine macrostructure compared to that refined by the commercial Al-Ti-B even in the short melt-treating time less than about 10 minute. In the cast of sufficient melt-treating time, both the commercial Al-Ti-B and the Al-8.6Ti-0.025C shows effective refining ability similar to Fig. 5(c).

Both TiAl_3 and TiC particles are known to act as substrates for heterogeneous nucleation of aluminum grains during solidification [3-4]. It is of interest to understand the effects and roles of TiAl_3 and TiC on nucleation. Maxwell and Hellawell have reported that the nucleation of aluminum requires little or no under-cooling in the presence of TiAl_3 as compared to TiC or TiB_2 , indicating that TiAl_3 is able to be suggested as a better nucleant than TiC or TiB_2 for $\alpha\text{-Al}$ [5]. Moreover, TiAl_3 is also known to have more number of planes that have a good orientation relationship with $\alpha\text{-Al}$ in comparison to TiC or TiB_2 . On the other hands, TiC particle is known to promote direct nucleation of $\alpha\text{-Al}$ when excessive Ti solute contributes as a strong constitutional super-coolant and retards grain growth [6]. Therefore, excessive Ti solute in molten alloy containing carbide particles is able to be expected to have a favorable effect on grain refinement. This could explain why the Al-8.6Ti-0.025C refiner showed effective grain refining ability comparable to the

commercial Al-Ti-B refiner. The result of a recent paper wherein Al-8.6Ti-0.025C refiner containing both TiAl_3 and TiC exhibits much better effect on refinement of $\alpha\text{-Al}$ than that containing only TiC [7], revealing the importance of excess Ti (beyond that combined in TiC).

4. Summary

An eco-friendly production technique of Al-8.6Ti-0.025C refiner was developed by melting a Al-Ti master alloy in a graphite crucible, in which the potential nucleation site, TiC effectively formed by the spontaneous in-situ reaction between excessive Ti and carbon from graphite crucible. The A3003 alloy refined by the Al-8.6Ti-0.025C showed effectively refined macrostructure and enhanced mechanical properties comparable to the commercial Al-Ti-B refiner. The effective refinement was achieved in a shorter compare to the melt-treating time commercial Al-Ti-B refiner.

References

- [1] A. Cibula: J. Inst. Met., 76 (1949/1950) 321-360
- [2] B. S. Murty, S. A. Kori and M. Chakraborty: International Materials Review, 47 (2002) 3-29
- [3] E. L. Grasson and E. F. Emely: "The Solidification of Metals", London: The Iron and Steel Institute (1968)
- [4] G. E. Bolling: "Solidification", Materials park, OH (1970)
- [5] I. Maxwell and A. Hellwell: Acta Metall., 23 (1975) 229-237.
- [6] A. Cibula: J. Inst. Met., 80 (1951/1952) 1-16
- [7] Z. Q. Wang, X. F. Liu, S. T. Li, X. F. Bian and J. Y. Zhang: Mater. Sci. Technol., 19 (2003) 1709-1714